

<i>Product</i>	<i>Description</i>	<i>Visible Light Transmitted</i>	<i>Visible Light Reflected</i>	<i>Solar Energy Transmitted</i>	<i>Solar Energy Reflectance</i>	<i>Solar Energy Absorbance</i>	<i>Total Solar Energy Rejected</i>	<i>Median "U" Factor</i>	<i>Design "U" Factor</i>	<i>Shading Coefficient</i>	<i>UV Rejection</i>	<i>Solar Heat Gain Coefficient</i>
<b>Designer Gray</b>												
DG-35	Designer Gray	38%	20%	33%	23%	44%	56%	1	1.04	0.51	99%	0.44
DG-45	Designer Gray	42%	13%	40%	15%	45%	49%	1.06	1.1	0.58	99%	0.50
DG-55	Designer Gray	51%	11%	47%	14%	39%	43%	1.07	1.11	0.66	99%	0.57
<b>Starlite</b>												
SL-280	Starlite	28%	33%	23%	35%	42%	66%	1.02	1.06	0.39	99%	0.34
SL-380	Starlite	37%	21%	32%	22%	46%	53%	1.09	1.13	0.54	99%	0.47
<b>Soft Bronze</b>												
SB-25	Soft Bronze	25%	32%	20%	40%	40%	70%	0.98	1.03	0.34	99%	0.30
SB-35	Soft Bronze	35%	26%	29%	32%	39%	61%	1.01	1.06	0.44	99%	0.38
<b>Safety</b>												
DG-35 4Mil	Designer Gray	38%	20%	33%	23%	44%	56%	1	1.04	0.51	99%	0.44
DG-45 4Mil	Designer Gray	42%	13%	40%	15%	45%	49%	1.06	1.1	0.58	99%	0.50
DG-35 8Mil	Designer Gray	38%	20%	33%	23%	44%	56%	1	1.04	0.51	99%	0.44
DG-45 8Mil	Designer Gray	42%	13%	40%	15%	45%	49%	1.06	1.1	0.58	99%	0.50
Specs on 1/8" glass												